



REDOIL

SCHEDA TECNICA



EELQMS

EUROPEAN ENGINE
LUBRICANTS QUALITY

MANAGEMENT SYSTEM
Data di prima emissione
19/11/2021

Rev. N°4 del 01/07/2024

ATF FLUITRONIC VW 6 MARCE

SPECIFICHE

VW G 055 005

BMW 83220144137/83220142516/83222305396

MASERATI 231603 JAGUAR F8432 LAND ROVER 500050



DESCRIZIONE TECNICA

Fully synthetic lubricant for automatic transmissions, specifically designed to meet the needs of the 6-speed VW. This category of automatic transmissions is characterized by very efficient operation that allows significant fuel and CO2 savings of up to 5 grams per kilometer. The special additive chemistry with low viscosity and extremely stable friction values highlights the remarkable characteristics of specificity for VW 6 RATIOS but also of application compatibility for the same category of transmissions mounted on BMW, MASERATI, JAGUAR and LAND ROVER.

The use of this product ensures:

Very high thermal and oxidative stability

Maximum energy efficiency

Fluid couplings

Maximum wear resistance

Maximum compatibility with the materials used in these systems

Low pour point

Maximum detergent action

Maximum anti-foam action

High anti-corrosion and anti-rust properties

For further details, please contact the technical office



Via Boscofangone, Zona industriale ASI

80035 – NOLA (NA) – ITALIA

Tel: 081 3151396/97

Fax: 081 3151605

Web: www.siralspa.it

laboratorio@siralspa.it

Responsabile di laboratorio





REDOIL



SCHEDA TECNICA

ATF FLUITRONIC VW 6 MARCE

Caratteristiche Tipiche

Proprietà	Unità	Metodo	Valori Medi
Colore	-	Visivo	Ambra
Aspetto	-	Visivo	limpido
Densità	Kg/dm3	ASTMD7042	0,845
Viscosità 40° C	cSt	ASTMD445	29
Viscosità 100° C	cSt	ASTMD445	6,05
Indice di viscosità	-	ASTMD2270	162
Flash Point	°C	ASTMD92	224
Punto di congelamento	°C	ASTMD97	-40

MODALITA' D'USO

Use according to the recommendations in the use and maintenance manual provided by the manufacturer. Store the product in a cool, dry place, away from direct sunlight and at temperatures no higher than 60°C.

SICUREZZA E AMBIENTE

Utilizzare in conformità alle raccomandazioni fornite nella Scheda di Sicurezza

Informazioni aggiuntive su MSDS



Via Boscofangone, Zona industriale ASI
80035 – NOLA (NA) – ITALIA
Tel: 081 3151396/97
Fax: 081 3151605
Web: www.siralspa.it
laboratorio@siralspa.it

Responsabile di laboratorio