



REDOIL



EELQMS
EUROPEAN ENGINE
LUBRICANTS QUALITY
MANAGEMENT SYSTEM
Data di prima emissione
07/03/2024

TECHNICAL DATA SHEET

HIDRUS HVI 68 SINT

PAO-ESTERE fully synthetic hydraulic lubricant

SPECIFICS

- ISO VG 68
- DIN 51524 PART 3 HVLP ISO 6743-4 ISO-L-HV/HS ISO 11158 HV
- US Parker Denison HF-0/1/2 Level
- Fives Cincinnati P69 (ISO 68) BS4231 HSE EATON VICKERS I-286/M2950-S
- Eaton Brochure 03-401-2010 SAE MS1004 SAWER -DANFOSS GM LS-2
- U.S. STEEL 127/136 BOSCH REXROTH RDE 90220 LINDE AISE 127 AFNOR NF 48603 HV

TECHNICAL DESCRIPTION

Fully synthetic HVI hydraulic fluid, obtained through a special synthesis process of the olefin molecule to obtain polymerised molecules with a longer chain and extreme resistance to oxidation and for safe use of the hydraulic fluid subjected to extreme pressure and temperature conditions.

The molecule structured using engineering techniques gives the lubricant exceptional properties in a natural way without having to resort to the use of improver or inhibitor additives that can give dirt and residue and reduce the life of the fluid.

The use of such a product ensures:

- Maximum energy efficiency;
- Very high viscosity index, so that it can operate even with large temperature fluctuations;
- Maximum stability to oxidation;
- Maximum cleanliness of the circuit;
- Excellent compatibility with materials;
- High anti-corrosion and anti-rust properties;
- High anti-foaming capacity;
- Excellent pumpability at low temperatures.



For further details, please contact the technical department



P.IVA/C.F.: 03903071219



Via Boscofangone, Zona industriale ASI
80035 – NOLA (NA) – ITALIA
Tel: 081 3151396/97
Fax: 081 3151605
Web: www.siralspa.it
laboratorio@siralspa.it

Responsabile di laboratorio

TECHNICAL DATA SHEET

HIDRUS HVI 68 SINT

Typical characteristics

Properties	Unit	Method	Average values
Density at 15°C	Kg/m ³	ASTM D 1298	858
Kinematic viscosity at 40°C	cSt	ASTM D 445	68
Kinematic viscosity at 100°C	cSt	ASTM D 445	11,0
Viscosity index	-	ASTM D 2270	153
Flash Point	°C	ASTM D 92	242
Pour point	°C	ASTM D 97	-48

MODE OF USE

Use in accordance with the recommendations in the user and maintenance manual supplied by the manufacturer. Store in a cool, dry place, protected from direct sunlight and at temperatures not exceeding 60°C (140°F).

SAFETY AND ENVIRONMENT

Use in accordance with the recommendations provided in the Safety Data Sheet. Additional information on MSDS.